



CHEMCURE II™

CHEMCURE II™

FUNCTION: CHEMCURE II™ is an activator designed for chemical cure style tank linings.

TYPICAL PHYSICAL PROPERTIES:	Color.....	Amber
	Wt./Gal.....	7.7 lbs.
	Specific Gravity.....	0.94
	Non-Volatile Solids.....	25-30%
	Shelf Life @ 75° F (24°C).....	1 yr. from DOS
	Flash Point.....	113° F
	Coverage-Sq. Ft./Gal./Coat.....	Approx. 475

DIRECTIONS FOR USE: CHEMCURE II™ application is made easy.

1. Shake solution well.
2. Apply two coats on installed lining.
3. Chemcure II should not be applied if rubber temperatures are below 50° F (10° C) or above 140° F (60° C). **Note:** at the low end the cure time may take months.

The second coat may be made after the first coat has partially been absorbed. CHEMCURE II™ cross-links at ambient temperature. Approximately one week is adequate to cure the chemically activated lining.

CHEMCURE II™ activated linings may be accelerated by exhaust steam at 160° to 180° F for 12 to 16 hours. It is best to allow CHEMCURE II™ to age for six hours before steam assisting the cure.

CHEMCURE II™ is FDA sanctioned for direct food contact.

TOXICITY: Prolonged breathing of vapors is harmful. Use only with adequate ventilation and an approved respirator. See MSDS for further instructions.

SAFETY: Usual fire safety measures should be observed. Keep away from heat, sparks and open flame.